PRODUCT SPECIFICATION SHEET BELZONA 4151

FN10006

GENERAL INFORMATION

Product Description:

A concrete protection system for the treatment of surfaces exposed to chemical attack and abrasion. Also for grouting and bonding. A two component clear amber resin system with excellent adhesion to masonry and metallic surfaces. Provides a tough seamless coating suitable for heavy duty dust proofing or protection from chemicals.

APPLICATION INFORMATION

Working Life

Will vary according to temperature. At 77°F (25°C), use all mixed material within 12 minutes.

Film thickness and coverage rate will vary with porosity and profile of the substrate. Each 4.95 kg unit will give a practical coverage rate of 167 sq.ft. (15.5 sq.m.).

Allow to solidify for the times shown in the Belzona IFU before subjecting it to the conditions indicated.

Volume Capacity

272 cu. in. (4455 cm³)/4.95 kg unit. 55 cu. in. (900 cm³)/kg.

Base Component

Clear Liquid **Appearance** Colour Light amber Viscosity 3.6-4.8 poise at 77°F (25°C) Density

1.16 g/cm³

Solidifier Component

Appearance Clear Liquid Color Amber 0.5-1.5 poise at 77°F (25°C) Viscosity 1.02 g/cm³ Density

Mixing Ratio

For mixing small quantities the mixing ratio of the components is:-Base: Solidifier 2.3:1 by weight: by volume: 2:1

The above application information serves as introductory guide only. For full application details including the recommended application procedure/technique, refer to the Belzona IFU which is enclosed with each packaged product.

ABRASION

Taber

When tested in accordance with ASTM D4060 with a 1kg load, typical loss per 1,000 cycles is:

Wet (H10 wheels) 890 mm³ Dry (CS17 wheels) 18 mm^3

CHEMICAL RESISTANCE

Belzona 4151 is resistant to a broad range of chemicals including: alkalis, hydrocarbons, detergent solutions, mineral and lubricating oils, salts and many other commonly found chemicals.

For a more detailed description of chemical resistance properties, refer to relevant Chemical Resistance chart.

The tensile shear adhesion to steel when tested in accordance with ASTM D1002 is typically 2,620 psi (18.1 MPa).

Positest Dolly Pull-Off (ASTM D4541)

900 psi (6.21 MPa)* Dry concrete Damp concrete 900 psi (6.21 MPa)* 1730 psi (11.93 MPa)* Dry brick 1690 psi (11.66 MPa)* Damp brick Dry quarry tiles 1470 psi (10.14 MPa)* 1430 psi (9.86 MPa)* Damp quarry tiles

*cohesive failure within substrate

Compressive Strength

The compressive strength of the material when tested to ASTM D695 is typically:

10.270 psi (70.8 MPa).

PRODUCT SPECIFICATION SHEET BELZONA 4151

FN10006



FLEXURAL PROPERTIES

Flexural Strength

The flexural strength of the material when tested to ASTM D790 is typically:

10,150 psi (70.0 MPa).

HEAT RESISTANCE

Heat Distortion Temperature (HDT)

Tested in accordance with ASTM D648 (264 psi fiber stress) is typically $106^{\circ}F$ ($41^{\circ}C$).

Dry Heat Resistance

The indicated degradation temperature in air based on Differential Scanning Calorimetry (DSC) operated in accordance with ISO11357 is typically 392°F (200°C).

For many applications the product is suitable down to -40°F (-40°C).

TENSILE PROPERTIES

Tensile Strength

The tensile strength of the material when tested to ASTM D638 is typically:

6,060 psi (41.8 MPa).

SHELF LIFE

Separate base and solidifier components shall have a shelf life of 5 years from date of manufacture when stored in their original unopened containers between 32°F (0°C) and 86°F (30°C).

WARRANTY

Belzona guarantees this product will meet the performance claims stated herein when material is stored and used as instructed in the Belzona Information For Use leaflet. Belzona further guarantees that all its products are carefully manufactured to ensure the highest quality possible and tested strictly in accordance with universally recognised standards (ASTM, ANSI, BS, DIN, ISO etc.). Since Belzona has no control over the use of the product described herein, no warranty for any application can be given.

AVAILABILITY AND COST

Belzona 4151 is available from a network of Belzona Distributors throughout the world for prompt delivery to the application site. For information, consult the Belzona Distributor in your area.

HEALTH AND SAFETY

Prior to using this material, please consult the relevant Material Safety Data Sheets.

MANUFACTURES

Belzona Polymerics Ltd. Claro Road, Harrogate, HG1 4DS. UK Belzona Inc. 2000 N.W. 88th Court, Miami, Florida, USA, 33172

TECHNICAL SERVICE

Complete technical assistance is available and includes fully trained Technical Consultants, technical service personnel and fully staffed research, development and quality control laboratories.

The technical data contained herein is based on the results of long term tests carried out in our laboratories and to the best of our knowledge is true and accurate on the date of publication. It is however subject to change without prior notice and the user should contact Belzona to verify the technical data is correct before specifying or ordering. No guarantee of accuracy is given or implied. We assume no responsibility for rates of coverage, performance or injury resulting from use. Liability, if any, is limited to the replacement of products. No other warranty or guarantee of any kind is made by Belzona, express or implied, whether statutory, by operation of law or otherwise, including merchantability or fitness for a particular purpose.

Nothing in the foregoing statement shall exclude or limit any liability of Belzona to the extent such liability cannot by law be excluded or limited.

Copyright @ 2016 Belzona International Limited. Belzona $^{\! \circ}$ is a registered trademark.

Belzona products are manufactured under an ISO 9001 Registered Quality Management System

