

PRODUCT SPECIFICATION SHEET

BELZONA 5851

FN10104



GENERAL INFORMATION

Product Description:

A single component coating based on a heat activated resin and corrosion resistant inert fillers. When cured, the material is durable and corrosion resistant. The system is specifically designed to be applied to hot surfaces 158 - 302°F (70 - 150°C), and is tolerant of surface preparation.

Application Areas:

When applied as detailed in the Belzona Instructions for Use (IFU), the system provides corrosion protection to steelwork covered with thermal insulation.

APPLICATION INFORMATION

Working Life

Cure will not commence until the product is heated, hence the working life of **Belzona 5851** is effectively unlimited.

Coverage Rate

Applied at a thickness of 8 mil (200 micron) a theoretical coverage rate of 25 sq.ft. (2.4 m²) per kg, per coat, should be achieved.

Cure Time

The cure time of **Belzona 5851** is dependent on the substrate temperature. Allow to cure for the times shown in the Belzona IFU before subjecting it to the conditions indicated.

Volume Capacity

29 in³ (476 cm³)/kg.

Mixed Properties

Appearance	Paste
Color	Gray
Gel strength at 68°F (20°C)	100 HF g/cm
Density	2.0-2.2 g/cm ³

The above application information serves as introductory guide only. For full application details including the recommended application procedure/technique, refer to the Belzona IFU which is enclosed with each packaged product.

PRODUCT SPECIFICATION SHEET

BELZONA 5851

FN10104



ADHESION

Tensile Shear

When tested in accordance with ASTM D1002, at elevated temperature (212°F/100°C), typical values will be:

2800 psi (19.3MPa) after cure at 212°F (100°C) applied onto clean, ground steel.

2800 psi (19.3MPa) after cure at 212°F (100°C) onto grit-blasted steel (min 75 μ profile).

1700 psi (11.7MPa) after cure at 212°F (100°C) applied onto rusty steel prepared to ISO 8501-1 St 2 (wire brushed)

2600 psi (17.9MPa) after cure at 212°F (100°C) applied onto rusty steel prepared to ISO 8501-1 St 3 (manually abraded)

CHEMICAL RESISTANCE

Once fully cured, the material will demonstrate excellent resistance to most commonly found inorganic acids and alkalis at concentrations up to 20%. The material is also resistant to hydrocarbons, mineral oils, lubricating oils and many other commonly found chemicals.

CORROSION RESISTANCE

Will show no visible signs of corrosion after 1,000 hours exposure in the ASTM B117 salt spray cabinet.

HARDNESS

Koenig Pendulum

When tested to ISO 1522 the Koenig damping time of the coating will be typically:

70 seconds after 7 days cure at 212°F (100°C)

HEAT RESISTANCE

Heat Distortion Temperature

Tested to ASTM D648 (264 psi fiber stress), typical value obtained will be:

260°F (127°C) after 7 days cure at 212°F (100°C)

Heat Resistance

For many typical applications, the product is thermally stable up to 302°F (150°C).

IMMERSION RESISTANCE

Immersion Resistance

When tested in accordance with ISO 2812-2, the coating, when applied to clean ground or grit blasted steel, will show no signs of failure after 6 months continuous immersion in artificial seawater at 104°F/40°C.

SHELF LIFE

Belzona 5851 will have a shelf life of 24 months from date of manufacture when stored in original unopened containers at 68°F (20°C). Refrigeration of this product will extend the shelf life.

PRODUCT SPECIFICATION SHEET

BELZONA 5851

FN10104



WARRANTY

Belzona guarantees this product will meet the performance claims stated herein when material is stored and used as instructed in the Belzona Information For Use leaflet. Belzona further guarantees that all its products are carefully manufactured to ensure the highest quality possible and tested strictly in accordance with universally recognised standards (ASTM, ANSI, BS, DIN, ISO etc.). Since Belzona has no control over the use of the product described herein, no warranty for any application can be given.

AVAILABILITY AND COST

Belzona 5851 is available from a network of Belzona Distributors throughout the world for prompt delivery to the application site. For information, consult the Belzona Distributor in your area.

HEALTH AND SAFETY

Prior to using this material, please consult the relevant Material Safety Data Sheets.

MANUFACTURER

Belzona Polymerics Ltd.
Claro Road, Harrogate,
HG1 4DS, UK

Belzona Inc.
2000N.W. 88th Court,
Miami, Florida, USA, 33172

TECHNICAL SERVICE

Complete technical assistance is available and includes fully trained Technical Consultants, technical service personnel and fully staffed research, development and quality control laboratories.

The technical data contained herein is based on the results of long term tests carried out in our laboratories and to the best of our knowledge is true and accurate on the date of publication. It is however subject to change without prior notice and the user should contact Belzona to verify the technical data is correct before specifying or ordering. No guarantee of accuracy is given or implied. We assume no responsibility for rates of coverage, performance or injury resulting from use. Liability, if any, is limited to the replacement of products. No other warranty or guarantee of any kind is made by Belzona, express or implied, whether statutory, by operation of law or otherwise, including merchantability or fitness for a particular purpose.

Nothing in the foregoing statement shall exclude or limit any liability of Belzona to the extent such liability cannot by law be excluded or limited.

Copyright © 2016 Belzona International Limited. Belzona® is a registered trademark.

*Belzona products are
manufactured under an
ISO 9001 Registered
Quality Management System*

